

EPHESUS FR

SURFACE / YÜZEY	BACKING / ZEMİN
VINYL / URETHANE TOP COAT VİNİL / POLİÜRETAN YÜZEY	%100 POLYESTER

TEST TYPES / TEST TİPİ	ASPECT / KRİTER	NORM	UNIT / BİRİM	STANDART TEST
WEIGHT / AĞIRLIK		680 ± 5%	g/m ²	ISO 2286-2
TENSILE STRENGTH / KOPMA DİRENCİ	ACROSS / EN	> 600	N	ISO 1421
	ALONG / BOY	> 400	N	ISO 1421
TEAR STRENGTH / YIRTILMA DİRENCİ	ACROSS / EN	> 50	N	ISO 4674-1
	ALONG / BOY	> 40	N	ISO 4674-1
ELONGATION AT BREAK / KOPMA ANINDAKİ UZAMA	ACROSS / EN	120 ± %20	%	ISO 1421
	ALONG / BOY	80 ± %20	%	ISO 1421
ADHESION / YAPIŞMA		> 40	N	ISO 2411
MARTINDALE - ABRASION / AŞINMA DİRENCİ		>75.000	RUB(12kPa)	ISO 5470-2
MARTINDALE - ABRASION / AŞINMA DİRENCİ		>100.000	RUB	ISO 12947-2
COLOR FASTNESS TO RUBBING / SÜRTÜNME RENK HASLIĞI	DRY / KURU	>= 5-6	GS	ISO 105X12
	WET / ISLAK	>= 5-6	GS	ISO 105X12
LIGHT FASTNESS / IŞIK HASLIĞI	LIGHT COLORS / AÇIK RENKLER	>= 5	BW	ISO 105B02
	DARK COLORS / KOYU RENKLER	>= 6	BW	ISO 105B02
ANTIMICROBIAL & ANTIFUNGAL / ANTİMİKROBİYAL & ANTİFUNGİ	E. Coli (Growth under sample)		Good Effect	ISO 20645:2002
	K. Pneumoniae (Growth under sample)		Good Effect	
	S. Aureus (Growth under sample)		Good Effect	
ANTIMICROBIAL ACTIVITY / ANTİMİKROBİYEL AKTİVİTE	S. Aureus (Growth under sample)		Good Effect	AATCC 147
WATERPROOF / SU GEÇİRMEZLİK	Hydrostatic head	OK	60 cm /per minute	BS 3424 Part 26
UREA RESISTANCE / ÜRE DAYANIMI	After 24 hours	No Significant Deterioration		BS 3424 Part 19
FLAME RETARDANCY / GÜÇ TUTUŞURLUK	IMO FTP Code Annex 1 Part 8 BS 7176 Low Hazard BS 5852 Part 1 Ignition Source 0,1 (Cigarette & Match) EN 1021 Part 1 and 2 DIN 4102 B2 French NFP 92 503 (M2) US: CAL TB 117-2013, Section E AT: ÖNORM B 3825, Gruppe 1 AT: ÖNORM A 3800 Teil 1 ECE R 118.03 Annex 6,7,8 FMVSS 302 (FR Standart of Motor Vehicles)			



FLOKSER

FLOKSER TEKSTİL SAN. VE TİC. A.Ş.

Hadımköy Mah. Ürgüplü Cad. No:7 34555 Arnavutköy / İSTANBUL - TÜRKİYE

+90 212 866 49 00 - 1258
+90 534 596 73 71

sales@floksertekstil.com.tr

floksertekstil.com.tr

/floksertekstil

