

SARTOR

TECHNICAL CHARACTERISTICS / TEKNİK ÖZELLİKLER

COMPOSITION/İÇERİK	BACKING/ZEMİN
VINYL / URETHANE TOP COAT VİNİL / POLİÜRETAN YÜZEY	%100 POLYESTER

TEST TYPES / TEST TİPİ	ASPECT / KRİTER	NORM	UNIT / BİRİM	STANDART TEST
WEIGHT / AĞIRLIK		500 ± 35	g / m ²	ISO 2286-2
MARTINDALE - ABRASION / AŞINMA DAYANIMI		> 75.000	RUB	ISO 5470-2
TEAR STRENGTH / YIRTILMA DİRENCİ	ACROSS / EN	> 20	N	ISO 4674-1
	ALONG / BOY	> 30	N	ISO 4674-1
TENSILE STRENGTH / KOPMA DİRENCİ	ACROSS / EN	> 240	N	ISO 1421
	ALONG / BOY	> 280	N	ISO 1421
ELONGATION AT BREAK / KOPMA ANINDAKİ UZAMA	ACROSS / EN	100 ± 20%	%	ISO 1421
	ALONG / BOY	95 ± 20%	%	ISO 1421
COLOR FASTNESS TO RUBBING / SÜRTÜNME RENK HASLIĞI	DRY / KURU	≥ 4	CS	ISO 105-X12
	WET / ISLAK	≥ 4	CS	ISO 105-X12
LIGHT FASTNESS / IŞIK HASLIĞI	LIGHT COLORS / AÇIK RENKLER	≥ 4	BW	ISO 105-B02
	DARK COLORS / KOYU RENKLER	≥ 5	BW	ISO 105-B02



FLOKSER

FLOKSER TEKSTİL SAN. VE TİC. A.Ş.

Hadımköy Mah. Ürgüplü Cad. No:7 34555 Arnavutköy / İSTANBUL - TÜRKİYE

+90 212 866 49 00 - 1258
+90 534 596 73 71

sales@floksertekstil.com.tr

floksertekstil.com.tr

/floksertekstil

